

**AC 28
MAGNATOP**

Typical Chemical Analysis

	%
Al ₂ O ₃	72.09
SiO ₂	25.66
TiO ₂	0.17
Fe ₂ O ₃	0.19
CaO/MgO	0.44
Na ₂ O/K ₂ O	0.53

Thermal Properties

Specific heat (J/kgK)	1000	
Thermal conductivity (W/mK)	1.6	(1300°C)
Coefficient of thermal expansion (K ⁻¹)	4.5 x 10 ⁻⁶	(25°C - 1400°C)

General Properties

Specific Resistance (Ωcm)	5 x 10 ⁵ - 3 x 10 ³	(800°C - 1400°C)
---------------------------	---	------------------

The above information is, to the best of our knowledge, correct at the time of writing, but is given without guarantee or responsibility since the conditions of use are beyond our control. Magna Industrials Ltd disclaim liability for loss or damage suffered from use of this data and no liability is accepted for use of this product which infringes any patent.